

TEST REPORT

MATERIAL : FKM 75 WHITE

COMPOUND NO. V7501W

A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS, SHORE A

TENSILE STRENGTH, Mpa,min

ELONGATION, % ,min

SPECIFIC GRAVITY

REQUIREMENTS

TEST RESULT

75+/-5 79

7.0 11.3

150 186

2.085

B)HEAT AGING @250 DEGREE C X 70 HRS.

HARDNESS CHANGE, POINTS

+10 +3

TENSILE STRENGTH CHANGE, %

-25 +19

ELONGATION CHANGE, %

-25 -18

C)COMPRESSION SET

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING@ 175 DEGREE C X 22 HRS, %,max

50 9

D)FUEL C OIL IMMERSION @RT X 70 HRS

HARDNESS CHANGE, POINTS

+/-5 -2

TENSILE STRENGTH CHANGE, %

-25 -2

ELONGATION CHANGE, %

-20 -4

VOLUME CHANGE, %

0 ~ +10 +3

NOTE: THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND V7501W CAN MEET ASTM D2000 M2HK807 A1-10 B37 EF31

QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08

