

TEST REPORT

MATERIAL : FKM 60 BROWN COMPOUND NO. :V6001N

A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS, SHORE A 硬度

TENSILE STRENGTH, MPa,min 拉力强度

ELONGATION, %,min 延伸率

SPECIFIC GRAVITY 比重

REQUIREMENT	TEST RESULT
60+/-5	61
7.0	7.6
200	363
	1.878

B) HEAT AGING @250 DEGREE C X 70 HRS.老化试验

HARDNESS CHANGE, POINTS 硬度变化

TENSILE STRENGTH CHANGE, %拉力强度变化率

ELONGATION CHANGE, %延伸率变化率

+10	+0
-25	+18
-25	-2

C) COMPRESSION SET 压缩永久变形试验

HEAT AGING @175 DEGREE C X 22 HRS, % max

50	11
----	----

D) FUEL C OIL IMMERSION @RT X 70 HRS 耐燃油 C 试验

HARDNESS CHANGE, POINTS 硬度变化

TENSILE STRENGTH CHANGE, %拉力强度变化率

ELONGATION CHANGE, %延伸率变化率

VOLUME CHANGE, %体积变化率

+/-5	-5
-25	-16
-20	-8
0~+10	+3

NOTE:THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND V6001N CAN MEET ASTM D2000 M2HK607 A1-10 B37 EF31



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08