

MATERIAL : EP 70 DURO FDA WHITE

COMPOUND NO. : E7011W

A) PHYSICAL PROPERTIES (PRESS CURE @170 DEGREE C X 10MIN)	Requirement	Test result
HARDNESS SHORE A 硬度	70+/-5	67
TENSILE STRENGTH, MPa,min 拉力強度	7.0	7.6
ELONGATION, % ,min 延伸率	200	308
SPEICFIC GRAVITY, 比重		1.244
B) HEAT AGING @100 DEGREE C X 70 HRS 老化試驗		
HARDNESS CHANGE, POINTS 硬度變化	+/-15	+3
TENSILE STRENGTH CHANGE, % 拉力強度變化率	+/-30	-14
ELONGATION CHANGE, % 延伸率變化率	-50	-11
C) COMPRESSION SET 壓縮永久變形試驗		
HEAT AGING @ 70 DEGREE C X 22 HRS % ,max	25	8

NOTE:1.THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND E7011W CAN MEET ASTM D2000 M8BA707 A14 B13 Z1(Z1=FDA)
2.THE COMPOUND IS COMPLY WITH FDA REGULATION ,BUT WE CAN NOT OFFER ANY
APPROVAL OR CERTIFICATION.



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08