



The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E) Songjiang
Shanghai China
POSTAL CODE: 201613
Tel:(021)57747878
Fax:(021)57747979
Website: <http://www.seal.com.tw>

TEST REPORT

MATERIAL : VT 80 BLACK COMPOUND NO. V8002B

A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS, SHORE A

TENSILE STRENGTH, MPa ,min

ELONGATION, %,min

SPECIFIC GRAVITY

REQUIREMENT	TEST RESULT
80+/-5	84
10.0	11.2
150	152
	1.795

B)HEAT AGING @250 DEGREE C X 70 HRS.

HARDNESS CHANGE, POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

+ 10	+ 2
-25	+4
-25	-15

C)COMPRESSION SET

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING @175 DEGREE C X 22 HRS, %,max

50	10
----	----

D) FUEL C OIL IMMERSION @RT X 70 HRS

HARDNESS CHANGE, POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

VOLUME CHANGE, %

+/- 5	- 2
-25	-21
- 20	- 16
0~+10	+ 3

NOTE:THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND V8002B CAN MEET ASTM D2000 M2HK810 A1-10 B37 EF31

QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08