

## TEST REPORT

MATERIAL : FFKM 75 Black HIGH TEMPERATURE 250°C

COMPOUND NO. : 9625B

### A)PHYSICAL PROPERTIES:

PRESS CURE @188 DEGREE C X 15 MIN

POST CURE 16hrs@200c,4hrs@230c,4hrs@250c,16hrs@270c

HARDNESS, PTS 硬度

TENSILE STRENGTH, Mpa 拉力強度

ELONGATION, % 延伸率

TEST RESULT

75

11.6

260

### B)COMPRESSION SET 壓縮永久變形試驗

HEAT AGING @ 200 DEGREE CX 70 HRS %

HEAT AGING @ 230 DEGREE CX 70 HRS %

20

26

NOTE: THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.  
THIS COMPOUND EKRAZ 9625B CAN MEET ASTM D2000 PERFLUOROELASTOMER  
REQUIREMENT.

PS:该材料是 3M 公司提供 (This compound is 3M company provide)

QC.Manager:Grace Chen

QC.Dept: Dolly Zhou

Test by: QC08