

TEST REPORT

MATERIAL : FFKM 70 WHITE HIGH TEMPERATURE 300°C

COMPOUND NO. : 9632W

A)PHYSICAL PROPERTIES:

PRESS CURE @188 DEGREE C X 15 MIN

POST CURE 16hrs@200c,4hrs@230c,4hrs@250c,16hrs@270c

HARDNESS, PTS

TENSILE STRENGTH, Mpa

ELONGATION, %

TEST RESULT

73

10.0

210

B)COMPRESSION SET

HEAT AGING @ 200 DEGREE CX 70 HRS %

HEAT AGING @ 230 DEGREE CX 70 HRS %

HEAT AGING @ 250 DEGREE CX 70 HRS %

23

25

28

NOTE: THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND EKRAZ 9632W CAN MEET ASTM D2000 PERFLUOROELASTOMER
REQUIREMENT.

QC.Manager: Grace Chen

QC.Dept: Dolly Zhou

Test by: QC08