

TEST REPORT

MATERIAL : FFKM 70 BLACK HIGH TEMPERATURE 290°C

COMPOUND NO. : 9652B

A)PHYSICAL PROPERTIES:

PRESS CURE @188 DEGREE C X 15 MIN

POST CURE 16hrs@200c,4hrs@230c,4hrs@250c,16hrs@270c

HARDNESS, SHORE A

TENSILE STRENGTH, Mpa ,min

ELONGATION, % ,min

REQUIREMENTS	TEST RESULT
70 ± 5	69
11	14.4
125	217

B)COMPRESSION SET

HEAT AGING @ 200 DEGREE CX 70 HRS %,max

25	20
----	----

C)NO.903 OIL RESISTANCE @ 150 DEGREE CX 70 HRS %,max

VOLUME CHANGE, % ,MAX

+10	+1.7
-----	------

NOTE: THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND EKRAZ 9652B CAN MEET ASTM D2000 PERFLUOROELASTOMER
REQUIREMENT.

QC.Manager:Grace Chen

QC.Dept: Dolly Zhou

Test by: QC08