

TEST REPORT

MATERIAL : FFKM 75 Black HIGH TEMPERATURE 300°C

COMPOUND NO. : 9655B

AS568-214

A)PHYSICAL PROPERTIES:

PRESS CURE @170~175DEGREE C X 700 "

POST CURE @230 DEGREE C X 12HRS

HARDNESS, SHORE A 硬度

TENSILE STRENGTH, Mpa,min 拉力強度

ELONGATION, % ,min 延伸率

SPECIFIC GRAVITY 比重

REQUIREMENTS	TEST RESULT
75 ± 5	79.4
11.0	13.0
125	201
	2.01

B)COMPRESSION SET 壓縮永久變形試驗

HEAT AGING @ 200 DEGREE CX 70 HRS %

--- 26

C)HEAT AGING @ 300 DEGREE C X 70 HRS 老化試驗

HARDNESS CHANGE , POINTS 硬度变化

TENSILE STRENGTH CHANGE , % 拉力强度变化率

ELONGATION CHANGE , % 延伸率变化率

+/-15	+2
+/-30	+2
-50	+18

NOTE: THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND EKRAZ 9655B CAN MEET ASTM D2000 PERFLUOROELASTOMER
REQUIREMENT.TEMPERATURE RANGE:-10°C~300°C.

QC.Manager:Grace chen

QC.Dept: Dolly Zhou

Test by: QC08

