

TEST REPORT

MATERIAL : FFKM 70 WHITE HIGH TEMPERATURE 230°C

COMPOUND NO. : 9697W

A)PHYSICAL PROPERTIES:

PRESS CURE @188 DEGREE C X 15 MIN

POST CURE 16hrs@200c,4hrs@230c,4hrs@250c,16hrs@270c

HARDNESS, PTS

TENSILE STRENGTH, Mpa

ELONGATION, %

TEST RESULT

72

13.6

169

B)COMPRESSION SET

HEAT AGING @ 200 DEGREE CX 70 HRS %

28

NOTE: THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND EKRAZ 9697W CAN MEET ASTM D2000 PERFLUOROELASTOMER
REQUIREMENT.

QC.Manager: Grace Chen

QC.Dept: Dolly Zhou

Test by: QC08