



ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E) Songjiang
Shanghai China
POSTAL CODE: 201613
Tel:(021)57747878
Fax:(021)57747979
Website: <http://www.seal.com.tw>

TEST REPORT

MATERIAL : FFKM 90 WHITE HIGH TEMPERATURE 230°C

COMPOUND NO. : 9699W

A)PHYSICAL PROPERTIES:

PRESS CURE @188 DEGREE C X 15 MIN

POST CURE 16hrs@200c,4hrs@230c,4hrs@250c,16hrs@270c

HARDNESS, PTS

TENSILE STRENGTH, Mpa

ELONGATION, %

TEST RESULT

86

19.4

140

B)COMPRESSION SET

HEAT AGING @ 200 DEGREE CX 70 HRS %

35

NOTE: THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND EKRAZ 9699W CAN MEET ASTM D2000 PERFLUOROELASTOMER
REQUIREMENT.

QC.Manager: Grace Chen

QC.Dept: Dolly Zhou

Test by: QC08