

MATERIAL : EP 90 DURO FDA WHITE

COMPOUND NO. : E9011W

	Requirement	Test result
A) RESS CURE @170 DEGREE C X 10MIN)		
HARDNESS SHORE A	90+/-5	85
TENSILE STRENGTH, MPa,min	7.0	9.0
ELONGATION, % ,min	100	267
SPEICFIC GRAVITY,		1.381
B) HEAT AGING @100 DEGREE C X 70 HRS		
HARDNESS CHANGE, POINTS	+/-15	+1
TENSILE STRENGTH CHANGE, %	+/-30	+2
ELONGATION CHANGE, %	-50	-7
C) COMPRESSION SET		
HEAT AGING @ 70 DEGREE C X 22 HRS % ,max	50	18

NOTE:1.THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND E9011W CAN MEET ASTM D2000 M2BA907 A14 B13 Z1(Z1=FDA)
2.THE COMPOUND IS COMPLY WITH FDA REGULATION ,BUT WE CAN NOT OFFER ANY
APPROVAL OR CERTIFICATION.

