

TEST REPORT**MATERIAL : NBR 80 DURO HIGH TEMP****COMPOUND NO. : N8062B****A) PHYSICAL PROPERTIES**

PRESS CURE @ 170 DEGREE C X 10 MIN

POST CURE @ 120 DEGREE C X 1 HR

HARDNESS , SHORE A

TENSILE STRENGTH, MPa ,min

ELONGATION, %,min

SPECIFIC GRAVITY

REQUIREMENT TEST RESULT

80+/-5 84

14 18.1

125 311

1.299

B) HEAT RESISTANCE @125°C X70HRS

HARDNESS CHANGE, POINTS

TENSILE CHANGE, %

ELONGATION CHANGE, %

0~+15 +1

-25 +4

-50 -42

C) COMPRESSION SET

CURING CONDITIONS

PRESS CURE @ 170 DEGREE C X 12 MIN

POST CURE @ 120 DEGREE C X 1 HR

HEAT AGING @ 100 DEGREE C X 22 HRS, % ,max

25 9

D)ASTM NO.1 OIL IMMERSION @125°C X70HRS

HARDNESS CHANGE , POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

VOLUME CHANGE, %

0~+10 +0

-20 -3

-35 -30

-15~+5 -2

E)ASTM IRM 903 OIL IMMERSION @125°C X70HRS

HARDNESS CHANGE , POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

VOLUME CHANGE, %

-10~+10 -9

-15 -6

-30 -30

0~+25 +9

NOTE:THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND N8062B CAN MEET ASTM D2000 M4CH814 A25 B14 EO15 EO35

QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08