

TEST REPORT

MATERIAL : FDA FKM 60 BLACK COMPOUND NO. V6011B

A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS, SHORE A 硬度

TENSILE STRENGTH, MPa,min 拉力强度

ELONGATION, %,min 延伸率

SPECIFIC GRAVITY 比重

REQUIREMENT	TEST RESULT
60+/-5	62
7.0	8.3
200	293
	1.797

B)HEAT AGING @250 DEGREE C X 70 HRS.老化试验

HARDNESS CHANGE, POINTS 硬度变化

TENSILE STRENGTH CHANGE, %拉力强度变化率

ELONGATION CHANGE, %延伸率变化率

+10	+0
-25	+2
-25	-8

C)COMPRESSION SET 压缩永久变形试验

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING @175 DEGREE C X 22 HRS, %.max

50	9
----	---

D) FUEL C OIL IMMERSION @RT X 70 HRS 耐燃油 C 试验

HARDNESS CHANGE, POINTS 硬度变化

TENSILE STRENGTH CHANGE, %拉力强度变化率

ELONGATION CHANGE, %延伸率变化率

VOLUME CHANGE, %体积变化率

+/-5	-4
-25	-24
-20	-20
0~+10	+5

NOTE:1.THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.

THIS COMPOUND V6011B CAN MEET ASTM D2000 M2HK607 A1-10 B37 EF31

2.THE COMPOUND IS COMPLY WITH FDA REGULATION ,BUT WE CAN NOT OFFER ANY APPROVAL OR CERTIFICATION.



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08