

TEST REPORT

MATERIAL : PEROXIDE NBR 50 DURO

COMPOUND NO. : N5021B

A)PHYSICAL PROPERTIES (PRESS CURE @170 DEGREE C X10min)	REQUIREMENTS	TEST RESULT
HARDNESS ,SHORE A	50+/-5	49
TENSILE STRETCH, MPa ,min	7.0	8.1
E L O N G A T I O N , % , m i n	3 5 0	4 5 5
SPECIFIC GRAVITY		1.213
B) HEAT RESISTANCE @100 DEGREE C X 70 HRS		
HARDNESS CHANGE, POINTS	+/-15	+1
T E N S I L E S T R E T C H C H A N G E , %	+ / - 3 0	- 1 5
E L O N G A T I O N C H A N G E , %	- 5 0	- 6
C) COMPRESSION SET 100 DEGREE C X 70 HRS		
SET , % ,max	25	9
D) NO. 1 OIL RESISTANCE @100 DEGREE C X 70 HRS		
H A R D N E S S C H A N G E , P O I N T S	- 5 ~ + 1 0	+ 6
T E N S I L E S T R E T C H C H A N G E , %	- 2 5	+ 3 0
E L O N G A T I O N C H A N G E , %	- 4 5	+ 1 1
VOLUME CHANGE, %	-10~+5	-8
E) NO. 3 OIL RESISTANCE @100 DEGREE C X 70 HRS		
H A R D N E S S C H A N G E , P O I N T S	- 1 0 ~ + 5	- 1
T E N S I L E S T R E T C H C H A N G E , %	- 4 5	- 3 8
E L O N G A T I O N C H A N G E , %	- 4 5	- 2 4
VOLUME CHANGE, %	0~+25	+1

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND N5021B CAN MEET ASTM D2000 M2BG507 A14 B14 EO14 EO34 Z1(Z1=FDA)

QA Manager: Grace Chen

QC.Dept:Dolly Zhou

