

TEST REPORT

MATERIAL : FKM 70 DURO BROWN COMPOUND NO. V7002N

A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS,SHORE A 硬度

TENSILE STRENGTH, MPa ,min 拉力强度

ELONGATION, %,min 延伸率

SPECIFIC GRAVITY 比重

REQUIREMENT	TEST RESULT
70+/-5	71
10	13.6
175	215
	2.025

B)HEAT AGING @250 DEGREE C X 70 HRS.老化试验

HARDNESS CHANGE, POINTS 硬度变化

TENSILE STRENGTH CHANGE, %拉力强度变化率

ELONGATION CHANGE, %延伸率变化率

+10	+3
-25	+1
-25	-11

C)COMPRESSION SET 压缩永久变形试验

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING @175 DEGREE C X 22 HRS, %,max

50	11
----	----

D) FUEL C OIL IMMERSION @RT X 70 HRS 耐燃油 C 试验

HARDNESS CHANGE, POINTS 硬度变化

TENSILE STRENGTH CHANGE, %拉力强度变化率

ELONGATION CHANGE, %延伸率变化率

VOLUME CHANGE, %体积变化率

+/-5	-2
-25	-17
-20	-9
0~+10	+4

NOTE:THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND V7002N CAN MEET ASTM D2000 M2HK710 A1-10 B37 EF31 Z1

QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08