



ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E) Songjiang
Shanghai China
POSTAL CODE: 201613
Tel:(021)57747878
Fax:(021)57747979
Website: <http://www.seal.com.tw>

TEST REPORT

MATERIAL : FFKM 75 BLACK HIGH TEMPERATURE 230°C

COMPOUND NO. : 9654B

AS568-214

A)PHYSICAL PROPERTIES:

PRESS CURE @170~168 DEGREE C X 15min

POST CURE @230 DEGREE C X 4hrs

HARDNESS, SHORE A 硬度

TENSILE STRENGTH, Mpa ,min 拉力强度

ELONGATION, % ,min 延伸率

SPECIFIC GRAVITY 比重

REQUIREMENTS	TEST RESULT
75 ± 5	80
11	17.0
125	138
	1.97

B)COMPRESSION SET 压缩永久变形试验

HEAT AGING @ 200 DEGREE C X 70 HRS %,max

--- 21

C)HEAT AGING @ 230 DEGREE C X 70 HRS 老化试验

HARDNESS CHANGE , POINTS 硬度变化

TENSILE STRENGTH CHANGE , % 拉力强度变化率

ELONGATION CHANGE , % 延伸率变化率

---- +4
---- -6
---- +19

NOTE: THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND EKRAZ 9654B CAN MEET ASTM D2000 PERFLUOROELASTOMER
REQUIREMENT. REQUIREMENT.TEMPERATURE RANGE:-10°C~230°C.

QC.Manager: Grace Chen

QC.Dept: Dolly Zhou

Test by: QC08

