

MATERIAL : EP 70 DURO GREEN

COMPOUND NO. : E7001G

A) PHYSICAL PROPERTIES (PRESS CURE @170 DEGREE C X 10MIN)	Requirement	Test result
HARDNESS SHORE A	70+/-5	69
TENSILE STRENGTH, MPa,min	8.0	10.7
ELONGATION, %,min	200	576
SPEICFIC GRAVITY,		1.279
B) HEAT AGING @100 DEGREE C X 70 HRS		
HARDNESS CHANGE, POINTS	+/-15	+4
TENSILE STRENGTH CHANGE, %	+/-30	-6
ELONGATION CHANGE, %	-50	-20
C) COMPRESSION SET		
HEAT AGING @ 70 DEGREE C X 22 HRS % ,max	25	21

NOTE:THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND E7001G CAN MEET ASTM D2000 M8BA708 A14 B13

QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08