

## TEST REPORT

MATERIAL: SILICONE 70 DURO GREEN      COMPOUND:S7049G

SPECIFICATION: PHYSICAL REQUIREMENTS OF ZZ-R-765, CLASS 2A, 2B, GRADE 70

**A) PHYSICAL PROPERTIES**

PRESS CURE @170 DEGREE C X 10MIN)

POST CURE@200 DEGREE C X 4HRS

	REQUIREMENT TEST RESULT	
	2A/2B	
HARDNESS PTS	70±5	69
TENSILE STRENGTH, MPa	4.48	5.3
ELONGATION, %	125 /80	128
SPECIFIC GRAVITY,		1.29

**B) HEAT AGING @225 DEGREE C X 70 HRS**

HARDNESS CHANGE, PTS	±10	+1.0
TENSILE STRENGTH CHANGE, %	-25	-8.0
ELONGATION CHANGE, %	-40	-29.0

**C) COMPRESSION SET:**

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20MIN

POST CURE @200 DEGREE C X 4HRS

HEAT AGING@150 DEGREE C X 70 HRS .%	40/25	19
-------------------------------------	-------	----

**D) AFTER WATER IMMERSION , 100 DEGREE C X 70 HRS**

VOLUME CHANGE, MAX PERCENT	+5	+4
----------------------------	----	----

E) LOW TEMPERATURE ,BRITTLE POINT	-62.2 deg c	NONBRITTLE
-----------------------------------	-------------	------------

NOTE: THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY  
THIS COMPOUND S7049G CAN MEET ZZR765-2A/2B

QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08