



ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E), Songjiang,
Shanghai China
POSTAL CODE: 201613
Tel: (021)57747878
Fax (021)57747979
Website: <http://www.seal.com.tw>

TEST REPORT

MATERIAL FDA: SIL 50 DURO RED

COMPOUND NO. S5011R

A) PHYSICAL PROPERTIES

PRESS CURE @170 DEGREE C X 10MIN

POST CURE @200 DEGREE C X 4 HRS

	REQUIREMENTS	TEST RESULT
HARDNESS, POINTS	50+/-5	50
TENSILE STRENGTH, MPA	6.0	6.7
ELONGATION, %	250	388
SPECIFIC GRAVITY		1.135

B) HEAT RESISTANCE @225 DEGREE C X 70 HRS

HARDNESS CHANGE, PTS	+10	+3.0
TENSILE STRENGTH CHANGE, %	-25	-11.0
ELONGATION CHANGE, %	-30	-5.0

C) COMPRESSION SET

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @200 DEGREE C X 4 HRS

HEAT AGING @ 175 DEGREE C X 22HRS, %	25	10
--------------------------------------	----	----

D) ASTM NO. 1 OIL @ 150 DEGREE C X 70 HRS

HARDNESS CHANGE, POINTS	0~-15	-2.0
TENSILE STRENGTH CHANGE %	-20	-11.0
ELONGATION CHANGE, %	-20	-7.0
VOLUME CHANGE, %	0~+10	+6.0

E) ASTM NO. 3 OIL @ 150 DEGREE C X 70 HRS

HARDNESS CHANGE, PTS	-30	-10.0
VOLUME CHANGE, %	+60	+24.0

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.

THIS COMPOUND S5011R CAN MEET ASTM D2000 M5GE506 A19 B37 EO16 EO36

Z1(Z1=FDA)