



ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E), Songjiang,
Shanghai China
POSTAL CODE: 201613
Tel: (021)57747878
Fax (021)57747979
Website: <http://www.seal.com.tw>

TEST REPORT

MATERIAL SIL 50 DURO WHITE

COMPOUND NO. S5001W

A) PHYSICAL PROPERTIES

PRESS CURE @ 170 DEGREE C X 10MIN

POST CURE @ 200 DEGREE C X 4 HRS

HARDNESS, SHORE A

TENSILE STRENGTH, MPa.min

ELONGATION, % ,min

SPECIFIC GRAVITY

REQUIREMENTS TEST RESULT

50+/-5 51

5.0 8.3

250 273

1.135

B) HEAT RESISTANCE @ 225 DEGREE C X 70 HRS

HARDNESS CHANGE, PTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

+10 +0

-25 -24

-30 -28

C) COMPRESSION SET

CURING CONDITIONS

PRESS CURE @ 170 DEGREE C X 20 MIN

POST CURE @ 200 DEGREE C X 4 HRS

HEAT AGING @ 175 DEGREE C X 22HRS, %,max

25 16

D) ASTM NO. 1 OIL @ 150 DEGREE C X 70 HRS

HARDNESS CHANGE, POINTS

TENSILE STRENGTH CHANGE %

ELONGATION CHANGE, %

VOLUME CHANGE, %

0~-15 -8

-20 -14

-20 -10

0~+10 +10

E) ASTM NO. 3 OIL @ 150 DEGREE C X 70 HRS

HARDNESS CHANGE, PTS

VOLUME CHANGE, %

-30 -18

+60 +54

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND S5001W CAN MEET ASTM D2000 M5GE505 A19 B37 EO16 EO36

QA Manager: Grace Chen

QC.Dept: Dolly Zhou

Test by: QC08