ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal Co., Ltd
No. 22, Beiyuan Road, Zhongli District
Taoyuan City 320023, Taiwan
Postal Code:320
Tel:886-3-451-5000
Fax:886-3-451-0123
Website: http://www.seal.com.tw

TEST REPORT

MATERIAL : EP 70 DURO PRO CURED RED COMPOUND NO: E7021R

Physical Properties (Press Cure:170℃X10min Post Cure:150℃X1h)	Requirement	Test result
Hardness,Point 硬度(邵A)	65.00~75.00	71.00
Tensile Strength,min,Mpa 拉力強度	7.00	7.30
Ultimate Elongation,min,% 延伸率	200.00	324.00
Specific Gravity, 比重		1.21
Heat Resistance 70h@125℃ 老化試驗		
Change in hardness,max,Point 硬度變化(邵A)	+10.00	+4.00
Change in tensile strength,max,% 拉伸強度變化率	-20.00	+22.00
Change in ultimate elongation,max,% 扯斷伸長率變化率	-40.00	-13.00
Compression Set 22h@125℃ 壓縮永久變形試驗		
Compression set,Method B,max,% 壓縮永久變形	70.00	12.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY

THIS COMPOUND E7021R CAN MEET ASTM 2000 M3CA707A25B35

QA Manager: John Ku **QC.Dept:** Dabou Ku **Test by:** QC08