



The Manufacturer of Sealing Parts

Escort Seal Co., Ltd
No. 22, Beiyuan Road, Zhongli District
Taoyuan City 320023, Taiwan
Postal Code:320
Tel:886-3-451-5000
Fax:886-3-451-0123
Website: <http://www.seal.com.tw>

TEST REPORT

MATERIAL : SIL 60 DURO BLACK

COMPOUND NO: S6001B

Physical Properties (Press Cure:170°CX10min Post Cure:200°CX4h)	Requirement	Test result
Hardness, Point 硬度(邵A)	55.00~65.00	63.00
Tensile Strength, min, Mpa 拉力強度	5.00	7.40
Ultimate Elongation, min, % 延伸率	200.00	321.00
Specific Gravity, 比重		1.23

Heat Resistance 70h@225°C 老化試驗

Change in hardness, max, Point 硬度變化(邵A)	+10.00	-2.00
Change in tensile strength, max, % 拉伸強度變化率	-30.00	-7.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-30.00	-16.00

Compression Set 22h@175°C 壓縮永久變形試驗

Compression set, Method B, max, % 壓縮永久變形	50.00	11.00
--	-------	-------

Fluid Resistance No.1 Oil Resistance 70h@150°C 1號油試驗

Change in hardness, Point 硬度變化	-15.00~0.00	-7.00
Change in tensile strength, max, % 拉力強度變化率	-20.00	+4.00
Change in ultimate elongation, max, % 延伸率變化率	-20.00	-6.00
Change in volume, % 體積變化率	0.00~15.00	+6.00

Fluid Resistance No.3 Oil Resistance 70h@150°C 3號油試驗

Change in hardness, Point 硬度變化	-35.00	-18.00
Change in volume, % 體積變化率	+60.00	+43.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND S6001B CAN MEET ASTM 2000 M4GE605A19B37EO16EO36