ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal Co., Ltd
No. 22, Beiyuan Road, Zhongli District
Taoyuan City 320023, Taiwan
Postal Code:320
Tel:886-3-451-5000
Fax:886-3-451-0123
Website: http://www.seal.com.tw

TEST REPORT

MATERIAL : FKM 70 DURO BROWN COMPOUND NO: V7001N

Physical Properties (Press Cure:170℃X10min Post Cure:230℃X24h)	Requirement	Test result
Hardness,Point 硬度(邵A)	65.00~75.00	74.00
Tensile Strength,min,Mpa 拉力強度	10.00	13.20
Ultimate Elongation,min,% 延伸率	175.00	233.00
Specific Gravity, 比重		2.01
Heat Resistance 70h@250℃ 老化試驗		
Change in hardness,max,Point 硬度變化(邵A)	+10.00	+1.00
Change in tensile strength,max,% 拉伸強度變化率	-25.00	-1.00
Change in ultimate elongation,max,% 扯斷伸長率變化率	-25.00	-6.00
Compression Set 22h@175℃ 壓縮永久變形試驗		
Compression set,Method B,max,% 壓縮永久變形	50.00	6.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY

THIS COMPOUND V7001N CAN MEET ASTM 2000 M2HK710A1-10B37

QA Manager: John Ku **QC.Dept:** Dabou Ku **Test by:** QC08