



The Manufacturer of Sealing Parts

Escort Seal Co., Ltd
No. 22, Beiyuan Road, Zhongli District
Taoyuan City 320023, Taiwan
Postal Code: 320
Tel: 886-3-451-5000
Fax: 886-3-451-0123
Website: <http://www.seal.com.tw>

TEST REPORT

MATERIAL : FKM 75 DURO BLACK

COMPOUND NO: V7501B

Physical Properties (Press Cure: 170°C X 10min Post Cure: 230°C X 24h)	Requirement	Test result
Hardness, Point 硬度(邵A)	70~80	73.30
Tensile Strength, min, Mpa 拉力強度	10.00	1883.00
Ultimate Elongation, min, % 延伸率	175.00	320.00
Specific Gravity, 比重		1.87

Heat Resistance 70h@250°C 老化試驗

Change in hardness, Point 硬度變化(邵A)	+10.00	+0.60
Change in tensile strength, max, % 拉伸強度變化率	-25.00	-3.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-25.00	+7.00
Change in volume, % 體積變化率		-2.80

Compression Set 22h@175°C 壓縮永久變形試驗

Compression set, Method B, max, % 壓縮永久變形	50.00	13.00
--	-------	-------

Fluid Resistance Fuel C Resistance 70h@23°C 燃油C試驗

Change in hardness, Point 硬度變化	±5.00	-3.30
Change in tensile strength, max, % 拉力強度變化率	-25.00	-5.00
Change in ultimate elongation, max, % 延伸率變化率	-20.00	+7.00
Change in volume, % 體積變化率	0.00~10.00	+3.60

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND V7501B CAN MEET ASMT 2000 M2HK710A1-10B37EF31